



Declaration of Performance

Heritage Soft Red
Reclamation Soft Red
Reclamation Weathered Soft Red
Midnight Red

Usage:	Facing clay masonry unit for internal or external use, load bearing or non-load bearing masonry structures.
Dimensional Tolerance:	+/- 2mm (1 sigma standard deviation from the mean as measured across 20 randomly chosen bricks.) DW4 as per AS/NZS 4455 and T1 as per BS EN771-1:2011.
Compressional Strength:	Mean 10.5 MPa Exceeds Australian standard for unconfined compressive strength as per AS/NZS 4455 along with European Standard BS EN771-1:2011.
Water Absorption:	Mean 13%
Durability:	General Purpose Brick
Active Soluble Salt Classification:	S2 As per BS EN771-1:2011 (Note: No Australian standard exists for soluble salt content of clay masonry units).
Freeze-Thaw Durability:	F2 (Suitable for Freeze-Thaw Climates) As per BS EN771-1:2011 (Note: No Australian standard exists for Freeze-Thaw durability for clay masonry units.)
Reaction to Fire:	A1 (No contribution to a fire) As per EN 13501-1 (Note: No Australian standard exists for reaction to fire for individual clay masonry units.)